

SIGRAFINE® MKUN

Material: Graphite

Forming: Vibration molded

Application: Industrial and electronic applications

Material data of SIGRAFINE® MKUN

Typical properties	Units	Test standards	Material data	
			Ø 760 ... 960 x 1000 mm Ø 1250 ... 1360 x 600 mm 610 x 720 x 2700 mm 630 x 1300 x 1420 mm	Ø 1550 x 600 mm Ø 1685 x 550 mm
Bulk density	g/cm ³	ASTM C559	1.67	1.66
Max. grain size	mm	DIN 66165	0.8	0.8
Resistivity	µΩm	DIN 51911	II	10
			I	12
Dynamic modulus of elasticity	GPa	DIN 51915	II	7
			I	6
Flexural strength (3 points)	MPa	DIN 51902	II	10
			I	9
Compressive strength	MPa	DIN 51910	II	25
			I	23
Tensile strength	MPa	DIN 51914	II	6
			I	6
Thermal expansion (20 – 200 °C)	10 ⁻⁶ K ⁻¹	DIN 51909	II	2.3
			I	3.2
Ash content	%	DIN 51903	0.07	0.07

II parallel to the grain direction; I perpendicular to the grain direction.

For any engineering/design purposes please always contact our technical sales team.



Graphite Materials & Systems | SGL CARBON GmbH
 Sales Europe/Middle East/Africa | gms-europe@sglcarbon.com
 Sales Americas | gms-americas@sglcarbon.com
 Sales Asia/Pacific | gms-asia@sglcarbon.com
www.fine-grain-graphite.com | www.sglcarbon.com

TDS MKUN1000.00

04 2019/0 E Printed in Germany

®registered trademarks of SGL Carbon SE

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should therefore not be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our "General Conditions of Sale".